



## Triton TANKING MIX ELASTIFIER (T.T.M.E)

### Description and Use

---

Triton T.T.M.E is a plasticizer-free anionic dispersion. It has excellent bonding and elongation properties with extremely low water absorption allowing Triton TT55 when mixed with Triton T.T.M.E. to be flexible waterproof coating suitable for either vertical or horizontal surfaces.

### Preparation

---

All surfaces to be treated with Triton T.T.M.E. must be free of all loose materials, dust, dirt, plaster, bitumen, oil, paint etc., and of a sound nature to allow maximum bonding to the original structure. This is best achieved by sand / shot blasting, scabbling or bush hammering. Once the surface has been prepared it should be pressure washed to remove any remaining dust.

### Application

---

TRITON T.T.M.E is ideal for use in areas, which are liable to cracking or deformation of the surface (not more than 0.5mm). Wall / floor junctions are areas in which Triton T.T.M.E can be successfully used.

A maximum of 4kg/sq metre can be applied in one layer. It can be applied with a trowel, brush or mortar gun.

DO NOT apply below 5°C.

### Consumption / Application Rate

---

2 coat application @ 6kg/m<sup>2</sup> (3kg/m<sup>2</sup>per coat).

### Areas of Use

---

As per Triton TT55 and additionally where vibration, cracking or minor movement is anticipated.

### Specification

---

NBS: Clause J10 110 Cementitious Mortar Tanking / Dampproofing.

### Mixing

---

Place 25kg of Triton TT55 into a clean container and add 10kg of Triton T.T.M.E. Mix thoroughly using a mechanical whisk for approximately 5 minutes.

### Storage

Protect from frost.

### Packaging

Packed in 10kg tubs.

### Health & Safety

For full information consult the relevant Material Safety Data Sheet.  
\*For chemical resistances please contact your Triton representative.

For further information please contact:

**Triton Chemical Manufacturing Co Ltd T/a Triton Systems**

Units 3 – 5 Crayford Commercial Centre, Greyhound Way, Crayford, Kent DA1 4HF

Tel: 01322 318830

Fax: 01322 524017

Email: [info@tritonsystems.co.uk](mailto:info@tritonsystems.co.uk)

[www.tritonsystems.co.uk](http://www.tritonsystems.co.uk)

Ref: Triton Tanking Mix Elastifier (T.T.M.E). 06/11